



# PQ Hollow Spheres



## Technical Datasheet Hollow Microspheres Q-Cel® 5020FPS

Product Designation	5020 FPS		
Composition	Inorganic sodium silicate borate		
Appearance	Free Flowing White Powder		
Physical Form	Spherical, non-porous.		
Bulk Density	0.11		
Effective Density (Liquid Displacement)	0.20 ± 0.02 g/cc	<i>Test Method: Visual ASTM D2840</i>	
Mean Particle Size (microns)	46	<i>Test Method: Malvern Particle Size Analyser</i>	
Distribution:	D10	16	
	D50	43	
	D90	76	
Crush Strength (volume loss)	10%	500 <b>PSI</b>	34 <b>Bar</b> 3.4 <b>MPa</b>
Heat Capacity	Kj/Kg. °C	1	
Thermal Conductivity	W/mK	0.057	
Refractive Index		1.5	
Chemical Resistance	Low alkali leach		

### Packaging

Hollow micro-spheres are supplied in a variety of packaging to meet customers' needs. Conditioning can be:

Boxes: 27.5 Kg

Bulk Bags: 175 Kg

### Safety Information

When using this product for prolonged periods in dusty environments inhalation may irritate the respiratory tract. NIOSH approved masks or respirators are recommended when handling the product.

Material Safety Data Sheets will be supplied on request.

### Storage:

The cartons, bags and boxes used to pack our micro-spheres are designed to protect damage during shipment and handling. Some cautions are given for a proper storage:

- Store micro-spheres containers in dry conditions.
- Partially used containers should be tightly closed, not left open to the atmospheres for extended periods.
- The products are hygroscopic and will tend to agglomerate upon prolonged exposure to moisture and humidity.

For further information about our range of Hollow Glass Microspheres, do not hesitate to contact us:

**Potters Europe – Engineered Glass Materials (EGM) Division**

Pontefract Road

Barnsley

South Yorkshire S71 1HJ

United Kingdom

Tel. +44 (0)1226 704514

Fax. +44 (0)1226 207615

E-mail: [PQHS-Sales@pottersgroup.com](mailto:PQHS-Sales@pottersgroup.com)

Website: [www.pottersgroup.com](http://www.pottersgroup.com)

The technical information presented herein is based on our best information available to us and is believed to be reliable. Potters Europe makes no warranties, either expressed or implied, with respect to our materials, including the warranties of merchantability or fitness for any particular purpose. We urge that users of our materials conduct tests to determine suitability for their specific end uses.

Potters Europe (EGM Division) and PQ Hollow Spheres are trading names of Potters Ballotini Limited and affiliated companies

Q-Cel®, Spherical®, Spheriglass®, Spheriwhite®, Glassfill®, Medisphere and Luxsil® are registered trademarks of Potters Industries Inc and affiliated companies

3-04-002-1-01.doc